


USG BORAL SECUROCK™ BRANDGLASS-MAT SHEATHING






WET AREA and EXTERIOR ENVELOPE





USG BORAL Securock™ GLASS-MAT PORTFOLIO

Exterior & Wet Area Applications



USG Boral Securock™ Glass-Mat Sheathing Regular and Firecode™ X

USG Boral Securock™ Brand Glass-Mat Sheathing is a non-combustible, moisture and mold resistant panel that offers a 100% inorganic fiberglass facer mat. Designed for use under exterior claddings where conventional gypsum sheathing products have traditionally been used or as substrate in properly detailed Exterior Finishing Systems (EIFS), Direct-Applied Exterior Finishing System (DEFS), clapboard siding, shingle siding, shake siding and conventional stucco.

Advantages:

Mold Resistant: High resistance to mold and mildew and scores a 10 (highest) when tested in accordance with ASTM D3273.

Resists Water: Glass-mat sheathing facer on both sides sheds water.

Fire Resistant: Extensive ANSI / UL 263 Fire Resistant Designs (UL Designation USGX)

Quick, Dry Installation: Quick score and snap, no sawing or special tools, and rapid screw or nail attachment.

Exposure: Can be exposed to weather for up to 12 months after application.

Warranted Performance: USG Boral Securock™ Glass-Mat Sheathing is guaranteed for five years against manufacturing defects and for 12 months of weather exposure. The manufacturing defect warranty could run up to 10 years when USG Boral Securock™ Glass-Mat Sheathing is installed as a substrate to a warranted EIFS/DEFS System. Consult USG Boral Limited Warranty for more details.



FEATURES & BENEFITS - Wet Area and Exterior Envelope

Non-Combustible, Water, Moisture and Mold Resistant

- 100% inorganic non-woven glass fiber scrim on both sides
- Patented Mold Tough™ technology with moisture and mold resistant gypsum core
- Non-combustible per BS 476 Part 4 and ASTM E136

Meets industry standard

- Approved for use by leading EIFS/DEFS companies
- Compliant with ASTM C1177 standards (Standard Specification for Glass-Mat Substrate for use as Sheathing)
- ICC-ES (International Code Council Engineering Services)
 Certification per IBC (International Building Code, 2015)
- Extensive ANSI / UL 263 Fire Resistant Designs (UL Designation USGX)

Quick Installation

- · Easy to score and snap
- · Accepts fasteners well

Warranted performance

- · Can be exposed to the weather for up to 12 months
- Guaranteed for five years against manufacturing defects
- Manufacturing defects up to 10 years when installed as a substrate to warranted EIFS/DEFS system
- Backed by the high-quality standards and outstanding service of USG Boral

Choice

- · Global manufacturing network
- 12.7mm (1/2") Securock™ Glass-Mat Sheathing Panel
- 15.9mm (5/8") Securock™ Glass-Mat Sheathing Panel





DESCRIPTION

ADVANTAGES

LIMITATIONS

PRODUCT DATA

USG BORAL SECUROCK™ BRAND

GLASS-MAT SHEATHING REGULAR AND FIRECODE™ X

Quality, high-performance sheathing for warranted protection from the elements

- · Treated gypsum core, combined with fiberglass face and back, offers exceptional water resistance
- · Scores and snaps easily for quick installation
- · For use in most exterior systems when properly detailed by exterior finish manufacturer
- · Meets or exceeds the requirements of ASTM C1177

USG Boral Securock™ Brand Glass-Mat Sheathing is a non-combustible, moisture and mold resistant panel designed for use under exterior claddings where conventional gypsum sheathing products have traditionally been used, such as brick veneer, properly detailed Exterior Insulation Finish Systems (EIFS), Direct-Applied Exterior Finishing System (DEFS), clapboard siding, panel siding, shingle siding, shake siding and conventional stucco.

Mold-Resistant: High resistance to mold and mildew and scores a 10 (highest) when tested in accordance with ASTM D3273.

Resists Water: Glass-Mat Sheathing facer on both sides sheds water.

Quick, Dry Installation: Quick score and snap, no sawing or special tools, and rapid screw or nail attachment.

Exposure: Can be exposed to weather for up to 12 months after application.

Warranted Performance: USG Boral Securock™ Glass-Mat Sheathing is guaranteed for five years against manufacturing defects and for 12 months of weather exposure. The manufacturing defect warranty could run up to 10 years when USG Boral Securock™ Glass-Mat Sheathing is installed as a substrate to a warranted EIFS/DEFS System. Consult USG Boral Limited Warranty for more details.

- 1. USG Boral Securock™ Glass-Mat Sheathing shall not be used as a nail base for exterior cladding.
- Specific requirements regarding framing spacing, fastener spacing and fastener specifics to provide required lateral wind-load resistance are the responsibility of the design professional. (Refer to technical data and specifications on the following pages.)
- 3. USG Boral Securock™ Glass-Mat Sheathing offers resistance to weather but is not intended for constant exposure to water. Protect this and all similar materials from the eroding efects of cascading water. If extreme weather conditions are possible, the design professional should consider recommending that panel joints be treated or a weather-resistant barrier be installed.
- 4. Not recommended for lamination to masonry surfaces. Use furring strips or framing.
- 5. Maximum stud spacing is 24" (610mm) centres.
- 6. USG Boral Securock™ Glass-Mat Sheathing is not a finished surface.

Dimensions: 1/2" (12.7mm) or 5/8" (15.9mm) thick, 48" (1219mm) wide, 8' (2438mm), 9' (2743mm) and 10' (3048mm) long. Up to 12' (3658mm) lengths available in 5/8" (15.9mm) thickness in some markets. Other sizes available on special order. Consult your USG Boral sales offce or representative for more information.

Weight: Approximately 2.0 lbs./sq. ft (9.8 kg/sqm) for 1/2" (12.7mm) thickness, 2.7 lbs./sq. ft. (13.2 kg/sqm) for 5/8" (15.9mm) thickness.

Edge Configuration: Square edges.

Compliance With Standards: Meets or exceeds the physical property requirements of ASTM C1177. 5/8" (15.9mm) USG Boral Securock™ Glass-Mat Sheathing is UL Classified as to fire resistance, surface-burning characteristics and core combustibility. ICC ES Evaluation Report ESR 3044.



PRODUCT DATA CONT.

Fire Performance: USG Boral Securock™ Glass-Mat Sheathing has a non-combustible core when tested in accordance with ASTM E136. Surface-burning characteristics—Flame spread 0, smoke developed 0, when tested in accordance with ASTM E84. Fire resistance—5/8" (15.9mm) panels meet the requirements of Type X as defined in ASTM C1396 and ASTM C1177 when tested in accordance with ASTM E119. UL Classified as to fire resistance. See Underwriters Laboratories Fire Resistance Directory for specific designs.

Tensile Bond: Exceeds 15 psi requirements for both cementitious and acrylic adhesives per ASTM C297.

Physical Properties Per ASTM C1177	1/2" (12.7mm) USG Boral Securock™ Brand Glass-Mat Sheathing Regular	5/8" (15.9mm) USG Boral Securock™ Brand Glass-Mat Sheathing Firecode™ X		
Weight, nominal, lbs./sq. ft. (kg/m2)	2.0 (9.8)	2.7 (13.2)		
Linear expansion with moisture change, in/in %RH	6.25 x 10 ⁻⁶	6.25 x 10-6		
Coeffcient of thermal expansion, in/in/°F (mm x mm x oc)	8.5 x 10 ⁻⁶ (15.3 x 10 ⁻⁶)	8.5 x 10 ⁻⁶ (15.3 x 10 ⁻⁶)		
Flexural strength, parallel, lbf. (N)	>80 (356)	>100 (444)		
Flexural strength, perpendicular, lbf. (N)	>107 (476)	>147 (653)		
R-Value, ft2•°F•hr/BTU (m2.K/W)	0.40	0.50		
Combustibility	Non-combustible	Non-combustible		
ASTM D3273 score	10/10	10/10		
Permeance, perms	29	28		
Surface burning characteristics (per ASTM E84 or CAN/ULC-S102): flame spread / smoke developed	0/0	0/0		
Humidified deflection, in. (mm)	<2/8" (<6.4)	<1/8" (<3.0)		
Bending radius (dry)*, ft. (mm)	9' (2743)	9' (2743)		

Due to the variability in environmental conditions of each installation, the framing and fastener spacing of curved walls should be reduced as the radius approaches the minimum allowed. At the minimum radius, it is recommended that fastener and frame spacing be 6" (152mm) centres.

Allowable Uniform Wind Load (Ibs./sq. ft.) for 1/2"-Thick Panels [kN/sqm for 12.7mm-Thick Panels]

Frame Spacing	Frame Spacing 12" (305mm)		16" (406mm)			24" (610mm)			
Fastener Spacing	4 (102mm)	6 (152mm)	8 (203mm)	4 (102mm)	6 (152mm)	8 (203mm)	4 (102mm)	6 (152mm)	8 (203mm)
Allowable Pressure	75 (3.59)	46 (2.20)	34 (1.63)	51 (2.44)	34 (1.63)	26 (1.24)	26 (1.24)	19 (0.91)	16 (0.77)

Allowable Uniform Wind Load (lbs./sq. ft.) for 5/8"-Thick Panels [kN/sqm for 15.9mm-Thick Panels]

Frame Spacing	12" (305mm)			16" (406mm)			24" (610mm)		
Fastener Spacing	4 (102mm)	6 (152mm)	8 (203mm)	4 (102mm)	6 (152mm)	8 (203mm)	4 (102mm)	6 (152mm)	8 (203mm)
Allowable Pressure	107 (5.12)	67 (3.21)	50 (2.39)	75 (3.59)	50 (2.39)	38 (1.82)	34 (1.63)	27 (1.29)	24 (1.15)

Notes: Applicable for both steel and wood framing. The values in this table are based on testing per ASTM E330 and represent the capacity of the sheathing to resist flexural failure or fastener pull-through with a 3.0 factor of safety. Capacities are based on a minimum fastener head diameter of 0.325" (8.3mm) (#6 bugle head screw). The withdrawal resistance of fasteners from framing is diferent on several factors, including but not limited to fastener type, fastener length and framing properties. The specification of fasteners is the responsibility of the Designer of Record. Manufacturer's recommendations are given below. These capacities assume continuous support of each stud flange over the full length of the sheathing panel. Allowable pressures are based on a maximum deflection limitation of L/360. Consult USG Boral representative for higher deflection limitations. Allowable pressure values are for short-term wind loads. Framing design is independent of these values. The design capacities of assemblies constructed with pneumatically driven fasteners are beyond the scope of this submittal sheet.

Moisture and Mold Resistance: USG Boral Securock™ Glass-Mat Sheathing resists moisture and mold and complies with ASTM C1177 for water resistance. In independent lab tests conducted on USG Boral Securock™ Glass-Mat Sheathing at the time of manufacture per ASTM D3273, Standard Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber, the panel score was 10.

This ASTM lab test may not accurately represent the mold performance of building materials in actual use. Given unsuitable project conditions during storage, installation or after completion, any building material can be overwhelmed by mold. To manage the growth of mold, the best and most cost-effective strategy is to protect building products from water exposure during storage and installation and after completion of the building. This can be accomplished by using good design and construction practices.



INSTALLATION

USG Boral Securock™ Glass-Mat Sheathing shall be installed in accordance with WB2451 USG Boral Securock™ Glass-Mat Sheathing Installation Guide, GA-253 Application of Gypsum Sheathing, and ASTM C1280 Standard Specification for Application for Application of Gypsum Panel Products for Use as Sheathing. If extreme weather conditions are possible, the design professional should consider recommending that panel joints be treated or a weather-resistant barrier be installed.

SPECIFICATIONS PART 1: GENERAL

1.1 Scope

Specify to meet project requirements.

1.2 Delivery and Storage of Materials

All materials shall be stored in an enclosed shelter providing protection from damage and exposure to the elements. Damaged or deteriorated materials shall be removed from the premises. Prior to installation, panels should be stacked flat (unless the contractor in charge of site safety directs otherwise to avoid point overloading of the structure or a tripping hazard) and reasonably protected from the elements.

Warning: Store all USG Boral Securock™ Glass-Mat panels flat. Panels are heavy and can fall over, causing serious injury or death. Do not move unless authorized. Panels 12' (3658mm) in length will in banded units. To ensure safety and performance of the product, use of a forklift truck with ship minimum 35" (889mm) span between the forks when moving the banded units is recommended. Keep the nylon bands on each lift until individual boards are moved.

PART 2: PRODUCTS

- A. USG Boral Securock™ Glass-Mat Sheathing—1/2" (12.7mm) or 5/8" (15.9mm) thick x 48" (1219mm) wide x 8'-10' (2438mm-3048mm) long (up to 12' (305mm) for 5/8" (15.9mm) thickness) with square edges.
- B. Screws—1-1/4" (32mm) or 1-5/8" (41mm) #6 bugle head corrosion-resistant fasteners. Where sheet-type weather-resistive barriers or self-adhering membranes are placed over the sheathing, corrosion resistance shall be equal to or greater than a hot-dipped galvanized coating of 460g/sqm of surface area. Where liquid or fluid-applied air and water barriers are used, or where no sheet-type weather-resistive barrier is used over the sheathing, screws shall have a corrosion resistance of more than 800 hours per ASTM B117. Stainless steel fasteners shall be used in coastal or aggressive environments. Consult the building code for other requirements.

PART 3: EXECUTION

3.1 Walls - Sheathing

- A. Apply weather-resistive or water barriers and flashing as required by and in accordance with the applicable local code requirements and the recommendations of the exterior cladding manufacturer, whichever is more stringent.
- **B.** Maximum fastener spacing for vertical surfaces is 8" (203mm) centres, unless limited by wind load restrictions or wood stud racking resistance requirements outlined in Product Data.
- C. Maximum frame spacing is 24" (610mm) centres.
- D. Sheathing must be thoroughly dry prior to installing adhesively applied and self-adhered ice / water barriers and joint tape. Failure to do so will result in an insuffcient bond to the sheathing.
- E. Apply side labeled "USG Boral Securock™" towards exterior. Fit ends and edges closely but not forced together.
- **F.** Fasteners shall be driven flush with the panel surface, without countersinking or deep enough to break the glass mat, and into the framing.
- G. Unless otherwise specified or required, USG Boral Securock™ Glass-Mat Sheathing may be applied either perpendicular or parallel to wood or steel framing.

3.1 Soffits - Sheathing Application

The maximum frame spacing for soffts is 16" (406mm) centres when installed parallel to the joists and 24" (610mm) centres when installed perpendicular to the joists. Maximum fastener spacing for horizontal surface (soffts) is 8" (203mm) centres.



SPECIFICATIONS CONT.

PART 3: EXECUTION

3.3 Control Joints

Control joints shall be installed at building expansion joints. Location and design of these control joints shall be detailed by the design professional. Per the International Building Code®, the distance between control joints shall not be more than 30' (9144mm).

3.4 Shear- or Fire-Rated Construction

Shear- or fire-rated construction may have additional execution requirements as specified in local codes or the UL Fire Resistance Directory.

3.5 Weather-Resistant Barriers

No weather-resistant barrier is required for exposure warranty but may be required by local codes or cladding system specifications.

3.6 Exterior Cladding Application

Consult exterior cladding manufacturer for installation instructions.

3.7 EIFS / DEFS

EIFS/DEFS, like all other cladding systems, is vulnerable to moisture that enters the cavity through wall penetrations, such as windows, doors, deck attachments and utility pipe chases, and at wall / roof intersections. For most residential and some commercial EIFS/DEFS system, manufacturers now specify a weather-resistive barrier for additional protection from moisture that penetrates the wall. In addition, manufacturers of windows, doors, flashing and sealants offer instruction on proper installation and maintenance of their products.

- EIMA (EIFS Industry Members Association), www.eima.com. This website has extensive information
 about proper installation of EIFS, sealants, flashing, proper attachment of EIFS to substrates, and
 inspection, maintenance and repair of EIFS claddings
- · ASTM E2112, Standard Practice for Installation of Exterior Windows, Doors and Skylights
- · ASTM C1481, Standard Guide for Use of Joint Sealants with EIFS
- ASTM C1397,Standard Practice for Application of Class PB EIFS

SUBMITTAL APPROVALS

Job Name		
Contractor	Date	



USG BORAL SECUROCK™ BRAND

GLASS-MAT SHEATHING

GENERAL

- 1.1 USG Boral Securock™ Brand Glass-Mat Sheathing meets or exceeds all requirements of ASTM C1177 Standard Specification for Glass-Mat Substrate for Use as Sheathing. Panels are available in 1/2"(12.7mm) and 5/8" (15.9mm) thicknesses, 48" (1219mm) wide, and standard lengths of 8' (2438mm), 9' (2743mm) and 10' (3048mm), with square edges. Other sizes are available on special order.
- 1.2 This product may be used under exterior claddings where conventional gypsum sheathing products have traditionally been used, such as brick veneer, clapboard, wood shingles or shakes, plywood, vinyl, metal and conventional stucco. This product may also be used as a substrate for mechanically and adhesively attached EIFS or DEFS applications.
- 1.3 Details and requirements pertaining to framing and application limitations shall be controlled by the cladding, structural or fire-resistant-rated system, and must be approved by the architect, engineer or design professional of record.
- 1.4 This product shall be installed in accordance with GA-253 Application of Gypsum Sheathing, ASTM C1280 Standard Specification for Application of Gypsum Sheathing and the requirements of USG Boral product literature.
- 1.5 This product is not approved for use as a nail base.
- 1.6 Details for construction of a specific assembly to achieve a required fire resistance shall be installed in accordance with actual fire-resistive testing. Consult the actual UL design and local fire test report for more details.
- 1.7 Where sound control is required, details of construction shall be in accordance with an acoustical test report of an assembly that has met the required acoustical value(s).
- 1.8 Where resistance to racking shear and/or transverse wind load is required, system-design capacities shall be obtained from USG Boral-published literature, engineering evaluations and test reports of a specific assembly where mandated by local code requirements.
- 1.9 Always wear appropriate personal protective equipment, such as gloves, safety glasses, hearing protection and a NIOSH-approved dust mask, when handling and installing USG Boral Securock™ Glass-Mat Sheathing panels.

DELIVERY AND JOB-SITE STORAGE

- 2.1 All materials shall be delivered in their original, unopened packages and stored in an enclosed shelter providing protection from damage and exposure to the elements.
 - **WARNING:** Store all USG Boral Securock™ Glass-Mat Sheathing panels flat, unless the site manager directs vertical stacking to avoid point overloading of the floor structure or a tripping hazard. Panels are heavy and can fall over, causing serious injury or death. Do not move unless authorized.
- 2.2 Prevent face, back and edges of the panels from exposure to cascading water.

FRAMING

- 3.1 USG Boral Securock™ Glass-Mat Sheathing shall be installed on either wood or steel framing. The framing system shall be sized and designed to meet the requirements of the intended application.
- 3.2 The maximum spacing for framing members is 24" (610mm) centres.
- 3.3 Framing shall be straight and true, attached securely following accepted engineering practices and as required for the intended design.
- 3.4 The surfaces to which abutting edges or ends of the sheathing are to be attached shall not be less than 1-1/4" (32mm) for steel framing and 1-1/2" (38mm) for wood framing.
- 3.5 Bearing surfaces shall not be less than 3/4" (19mm) for internal corners or angles.
- 3.6 Framing members shall be installed so that the surface will be on an even plane, unless otherwise specified, after the sheathing has been applied. The fastening surface shall not vary more than 1/8" (3mm) from the plane of the faces of adjacent framing members.

SHEATHING CUTTING AND APPLICATION

- 4.1 USG Boral Securock™ Glass-Mat Sheathing may be applied with long dimensions parallel or perpendicular to framing members except where limited by specific requirements. Sheathing orientation may be governed by local code or by the requirements of shear or fire-rated construction. Consult local codes and site-specific construction documents to ensure such requirements are met for every assembly prior to construction.
- 4.2 USG Boral Securock™ Glass-Mat Sheathing shall be cut to size by scoring the face mat with a utility knife from the face side, or by sawing. Separate by snapping the panel away from the score line to fracture the core and then by scoring the back mat with a utility knife. If a power saw is used, a cordless, low-rpm saw will generate less airborne debris than a corded power saw.
- 4.3 The cut edges and ends of the sheathing shall be trimmed to obtain neat-fitting joints when installed
- 4.4 Holes for pipe penetrations, fixtures or other small openings shall be scored or saw-cut from the face side before removing the cut-out.
- 4.5 Install panels with the logo side out. Panels are labeled "this side out" along the edge that must be visible from the exterior side of the assembly when installed properly.
- 4.6 All vertical ends and edge joints shall abut over the centers of framing members and shall be offset a minimum of one framing bay between adjacent rows of sheathing panels.
- 4.7 Center panel joints on framing members. Fit panels closely at edges and ends, but do not force together. Hold panels in firm contact with framing members and secure with fasteners as specified. Fasteners shall be driven flush with the panel surface—without countersinking or being deep enough to break the glass mat—and into the framing. Fasten the panel to framing, working from the center of the panel toward the edges and ends.
- 4.8 Screw profile must be designed for the framing in use, unless superseded by a more stringent specification. The minimum requirements for sheathing fasteners shall be as follows:
 - a. Screws: (1-1/4") (32mm) to (1-5/8") (41mm) #6 bugle head corrosion-resistant fasteners.
 - b. Corrosion Resistance: Where sheet-type weather-resistive barriers or self-adhering membranes are placed over the sheathing, corrosion resistance shall be equal to or greater than a hot-dipped galvanized coating of 1.5 ounces of zinc per square foot of surface area (457g/sqm). Where liquid- or fluid-applied air and water barriers are applied to the sheathing, or where no sheet-type weather-resistive barrier is used, screws shall have a corrosion resistance of more than 800 hours per ASTM B117. Stainless steel fasteners may be used in coastal or aggressive environments.
 - c. Edge Distance: The minimum distance from any fastener to the edge or end of the panel is 3/8" (9.5mm).
 - d. Spacing: Maximum fastener spacing is 8" (203mm) centres.
- 4.9 Supplementary use of panel adhesive will strengthen the connection and bridge minor irregularities between the panel and framing, facilitating enhanced performance and appearance. The use of adhesive, however, will not reduce the number of fasteners required by the specification. For optimal bond, apply adhesive in accordance with manufacturer's instructions. Framing must be free from oil and dirt, and sheathing must be clean and dry.
- 4.10 Fit sheathing snugly around window and door openings. Sheathing joints shall be offset a minimum of 4" (102mm) from the edge of any opening.
- 4.11 Sheathing shall be flashed at all openings (head, sill, etc.) and all roof / wall intersections (step, kickout, etc.) so water intrusion will not contact the sheathing.
- 4.12 Sheathing shall be no less than 8" (203mm) from the finish grade in weather and water protected siding, and no less than 12" (305mm) from the ground when used in correctly drained and vented crawl spaces.

SOFFIT CONSTRUCTION

- 5.1 The roof must be dried-in prior to the installation of sheathing in horizontal applications.
- 5.2 Maximum fastener spacing for soffits is 8" (203mm) centres.
- 5.3 Panels are subject to expansion and contraction due to changes in temperature and humidity. A 1/4" (6.35mm) clearance joint (perimeter relief) is required between USG Boral Securock™ Glass-Mat Sheathing installed in soffits and adjacent walls, fascia, beams or columns. Wings of "L", "U" and "T"-shaped areas should be separated with control joints. See the Control Joints section of this publication for additional requirements.
- 5.4 Adequate ventilation in accordance with the local code requirements shall be provided for the space immediately above the panels.
- 5.5 Applications must be designed to resist wind uplift. Contact USG Boral for a tailored design.
- 5.6 Fascia boards should extend at least 1/4" (6.35mm) below the ceiling board or adjacent trim moldings, whichever is lower, to provide a drip edge.

Option 1

Apply a synthetic-type direct-applied finish system in accordance with the finish manufacturer's recommendations.

Option 2

Apply USG Boral's 3 coat joint system by first embedding USG Boral Paper Joint Tape in USG Boral Setting-Type Joint Compound over all joints, achieving 300mm in width for a flatter finish. Upon setting, apply the second coat to be 100mm wider than the first and the finishing coat a further 100mm wider with USG Boral Setting Type Joint Compound.

Once dry, apply a smooth, uniform coat of USG Boral Setting-Type Joint Compound over the entire surface of the panels. Setting-type joint compound should be applied thick enough to ensure proper hydration prior to setting. For ease of application, USG Boral Setting-Type Joint Compounds with a longer setting time is recommended.

After the joint compound has dried, apply one coat of a good quality latex flat exterior primer and finish with two coats of a balanced, good-quality alkyd or latex exterior finish paint.

TILE BACKER CONSTRUCTION

- 6.1 Install backerboard with ends and edges closely abutted but not forced together. Stagger end ioint in successive courses.
- 6.2 For wall application, fasten USG Boral Securock™ Glass-Mat Sheating panels to framing with specified fasteners. Drive fasteners into field of panels first, working toward ends and edges.
- 6.3 Hold panels in firm contact with framing while driving fasteners. Ensure to space fasteners a maximum of 8" (203mm) for walls and 6" (152mm) for ceilings, with perimeter fasteners at least 3/8" (9.5mm) and less than 5/8" (15.9mm) from ends and edges. Drive screws to bottom of heads are flush with panel surface and do not over drive fasteners.
- 6.4 Ensure the use of approved fasteners.
- 6.5 Prefill joints and then immediately embed USG Boral Joint Mesh Tape before levelling joints.
- 6.6 Maintain 1/4" (6.4mm) gap between USG Boral Securock™ Glass-Mat Sheating to the tub surround.
- 6.7 Panels should be cut to size with a knife and straight edge. A power saw should be used only if it is equipped with a dust-collection device. Installer should wear NIOSH/MSHA-approved dust mask.

CONTROL JOINTS

- 7.1 The location and design of control joints are the responsibility of the design professional of record.
- 7.2 Control joints are required by the *International Building Code*. The maximum distance between control joints shall not exceed 30' (9144mm), and shall be installed at every building construction joint.
- 7.3 Locate all other control joints as per cladding system requirements or in accordance with ASTM C1280 Standard Specification for Application of Gypsum Sheathing, whichever is more stringent.

CLEAN UP

EXPOSURE AFTER INSTALLATION

PRODUCT INFORMATION

See USGBoral.com for the most up-to-date product information.

CAUTION

Dust may cause irritation to eyes, skin, nose, throat, and upper respiratory tract. Cut and trim with a utility knife or hand saw to minimize dust levels. Power tools must be equipped with a dust collection system. Wear eye, skin, and respiratory protection if necessary. If eye contact occurs, flush thoroughly with water for 15 minutes. If irritation persists, call a physician. Do not swallow. If swallowed, call a physician. Refer to USGBoral.com for Safety Data Sheet and other additional information.

KEEP OUT OF REACH OF CHILDREN.

TRADEMARKS

The trademarks USG BORAL and INNOVATION INSPIRED BY YOU are trademarks of USG Boral Building Products or one or more its affiliates.

NOTE

Products described here may not be available in all geographic markets. Consult your USG Boral sales office or representative for information.

SAFETY FIRST!

This technical information is intended to provide general information and should not be a substitute for professional building advice. We recommend you use a qualified person to install USG Boral products. Illustrations in this guide are only representative of USG Boral products and the appearance and effects that may be achieved by their use. To ensure the information you are using is current, USG Boral recommends you review the latest building information available on the USG Boral website USGBoral.com

Follow good safety/industrial hygiene practices during installation. Wear appropriate personal protective equipment. Read SDS and literature before specification and installation.

- 8.1 Leftover material shall be removed from the job site.
- 8.2 Waste material shall be disposed of in a safe manner and in compliance with site, local, state and/or federal requirements.
- 9.1 USG Boral Securock™ Glass-Mat Sheathing shall be covered by an exterior cladding or other weather-resistive barrier and is not intended for long-term exposure. Sheathing shall not be exposed to the elements for more than 12 months after it has been installed. Immediately upon installing the panels, the joints should be finished and the entire panel covered with a weather-resistive barrier if the exposure time will be more than 12 months.
- 9.2 Apply weather-resistive or water barriers and flashing as required by and in accordance with the applicable local code requirements and the recommendations of the exterior cladding manufacturer, whichever is more stringent.
- 9.3 For maximum protection, the design professional may recommend treating the cut edges with a low-modulus silicone sealant; treat joints by embedding 4" (102mm)-wide USG Boral Durock™ Brand Exterior Tape in a low-modulus silicone sealant and strike joints flush using a trowel or broad knife. Allow sealant to cure per manufacturer's instructions prior to installation of weather resistive barrier and/or cladding system.

NOTE: This treatment should be used only under mechanically attached weather-resistive barriers and cladding systems.

Manufactured by USG Boral Building Products Sdn Bhd Persiaran Lagoon, Bandar Sunway, Petaling Jaya, Selangor, Malaysia 46150 BCC XXXXX/07-2015 © 2015 USG Boral. All rights reserved.

USG BORAL SINGAPORE

8 Boon Lay Way #02-06 TradeHub 21 Singapore 609964 Tel: (65) 6272 9272 Fax: (65) 6278 5310 USGBoral.com

USG Boral Sdn. Bhd. (Singapore Branch) doing business as USG Boral Singapore

